

Direct-to-Mold PA66 Resins

RAPID CYCLING. RELIABLE MOLDING.

INVISTA's unreinforced direct-to-mold PA66 resins feature internal and external lubrication for consistent productivity, while delivering the toughness, chemical resistance and long-term heat resistance for which PA66 is known. With heat-stabilized and nucleated grades available, these resins are an ideal solution for a wide range of injection molding applications in transportation, electrical/electronic, industrial and consumer markets.

Benefits

- High flow
- V-2 flammability rating
- Heat resistance
- Chemical resistance
- High strength, excellent toughness
- Rapid crystallization allowing fast cycle times

Applications

ELECTRICAL/ELECTRONICS

- Terminal blocks
- Switches
- Connectors
- Thin-walled parts

SUITABLE GRADES

- PA66 U4630HSL
- PA66 U4820L

INDUSTRIAL

- Cable ties
- Fasteners

SUITABLE GRADES

- PA66 U4630HSL
- PA66 U4820L

TRANSPORTATION

- Canisters
- Wire management
- Fuse boxes

SUITABLE GRADES

- PA66 U4630HSL
- PA66 U4820L

CONSUMER

- Battery seals
- Kitchenware
- Lighters
- Aerosol valves

SUITABLE GRADES

- PA66 U4840NL
- PA66 U4820L

INVISTA Nylon Polymer

INVISTA is a global leader in the production of nylon intermediates and polymer resins. For more than 45 years, we've made nylon polymers that serve as the foundation for many different products across multiple markets including automotive, industrial, apparel and consumer electronics industries, to name just a few.

We are committed to helping our customers overcome their challenges and meet their objectives by providing the right resins and ingredients for their needs. Looking toward the future, we are continuing to strengthen our capabilities by investing in new ADN facilities.

Summary of Properties and UL Certifications

INVISTA PA66 Direct-to-Mold Resins						
Product Attribute			Lubricated	Heat-Stabilized	Ultra-Fast Cycle	
Property	Method	Unit	U4820L	U4630HSL	U4840NL	
PHYSICAL	Density	ISO 1183	g/cm ³	1.14	1.14	1.14
	Water Absorption - 24 Hours	ISO 62	%	1.8	1.7	1.4
	Melting Temperature	ISO 11359	°C	261	261	263
	Mold Shrinkage, 2.0 mm, Parallel	ISO 294-4	%	1.5	1.8	1.4
	Mold Shrinkage, 2.0 mm, Transverse	ISO 294-4	%	1.8	1.7	1.5
MECHANICAL (DAM)	Tensile Strength at Yield	ISO 527	MPa	82	84	93
	Elongation at Yield	ISO 527	%	4.2	4.2	4.0
	Elongation at Break	ISO 527	%	35	30	15
	Tensile Modulus	ISO 527	MPa	3200	3100	3700
	Notched Charpy at 23°C	ISO 179	kJ/m ²	5.5	5.0	3.7
	Notched Charpy at -30°C	ISO 179	kJ/m ²	4.3	4.2	3.1
	Unnotched Charpy at 23°C	ISO 179	kJ/m ²	Non-Break	Non-Break	Non-Break
	Unnotched Charpy at -30°C	ISO 179	kJ/m ²	Non-Break	Non-Break	Non-Break
	Notched Izod at 23°C	ISO 180	kJ/m ²	5.4	5.0	4.7
CERTIFICATION	UL - Flammability	UL 94	-	V-2 (0.40 mm)	V-2 (0.40 mm)	V-2 (0.40 mm)
	UL - RTI Elec / Imp / Str	UL 764	°C	130 / 65 / 75 (0.40 mm)	140 / 105 / 120 (0.40 mm)	130 / 65 / 75 (0.40 mm)
	UL - CTI	IEC 60112	Volts	600	600	600

Request a Sample Today

INVISTA Direct-to-Mold PA66 resins are available for sampling and qualification.

Contact us today at nylonpolymer.invista.com/contact to learn how INVISTA can support your material needs.

This Product Data Sheet relates only to the identified products and any identified uses. It is based on information available as of April 2021. Additional information may be needed to evaluate other uses of the product(s), including use of the product(s) in combination with any materials or in any processes other than those specifically referenced.

THIS PRODUCT DATA SHEET DOES NOT CONTAIN A COMPLETE STATEMENT OF, AND DOES NOT CONSTITUTE A REPRESENTATION, WARRANTY OR GUARANTY WITH REGARD TO, A PRODUCT'S CHARACTERISTICS, USES, QUALITY, MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR THE SUITABILITY, SAFETY, EFFICACY, HAZARDS OR HEALTH EFFECTS OF THE PRODUCT, WHETHER USED SINGULARLY OR IN COMBINATION WITH ANY OTHER PRODUCT, EXCEPT TO THE EXTENT REQUIRED BY THE RELEVANT LAW AND REGULATIONS. Nothing contained in this Product Data Sheet shall be construed to modify any of the terms under which the product(s) was sold by INVISTA. INVISTA and design are trademarks of INVISTA. © 2021 INVISTA. All rights reserved.